

DYNACOLL® S 1402

45.13.066e / 05.11

General Description

Saturated, linear copolyester, slightly crystalline.

Application

Solvent based adhesives and thermoplastic hotmelts, e.g. for profile wrapping and laminating applications.

Supply Form / Packaging

Granules in 20 kg paper-bags.

Specification

Property	Value	Unit	Test method
Viscosity number	73 - 83	cm ³ /g	DIN 53 728
Melting point (optical)	89 - 99	°C	Degussa-method
Acid number	≤ 3	mg KOH/g	DIN EN ISO 2114
Hydroxyl number	4 - 10	mg KOH/g	DIN 53 240-2

Typical data

Glass transition temperature (DSC) ¹⁾	- 10	°C	DIN 53 765
Softening point (Ring & Ball)	100	°C	DIN ISO 4625
Melt flow rate 160 °C (MFR)	100	g/10 min	DIN ISO 1133 (21.6 N)
Melt viscosity 160 °C	80	Pa s	(Plate/Plate)
Open time	15	s	Degussa-method
Tensile strength	10	N/mm ²	DIN EN ISO 527-1/3
Density	1.2	g/cm ³	DIN 53 479

¹⁾ Differential scanning calorimetry

Solubility

Soluble in chlorinated hydrocarbons, limited soluble in aromatics and toluene/MEK mixture.

Others

After application it is possible that the surface remains tacky, after crystallisation at approx. 50 °C the surface is non-blocking.

Storage Stability

Excluding sunlight and humidity S 1402 is stable at storage temperatures below 25 °C for at least 12 months.

Safety and Handling

Please refer to our Safety Data Sheet.

Evonik Resource Efficiency GmbH	Evonik Corporation	Evonik Degussa (China) Co. Ltd.
Paul-Baumann-Str. 1	Resource Efficiency	Resource Efficiency
45764 Marl	299 Jefferson Road	55 Chundong Rd., Xinzhuang Ind. Park
Germany	Parsippany, NJ 07054-0677, USA	Shanghai 201108, P.R. China
PHONE +49 2365 49-02	PHONE +1 973 929-8000	PHONE +86 21 61191-027
FAX +49 2365 49-5030	FAX +1 973 929-8460	FAX +86 21 61191-254

Email adhesives@evonik.com

www.evonik.com/adhesives-sealants

www.evonik.com/designed-polymers

Replaces leaflet 45.13.066e / 07.02 and all former issues
Marl, May 27, 2011

DYNACOLL® is a registered trademark of Evonik Industries AG or one of its subsidiaries

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.