

## Product information

# VESTALITE® S 101

(PRELIMINARY)

## GENERAL DESCRIPTION

VESTALITE® S 101 is a curing agent for epoxy resin matrix designed for SMC applications. Systems using VESTALITE® S 101 have a low initial viscosity during compounding, allowing excellent fiber wetting, high fiber volume fraction and efficient processing. The high reactivity of the hardener allows fast curing in about 4 - 5 min at 150 °C.

## SPECIFICATION

Tab.1: Properties of the neat resin system

	Unit	VESTALITE® S 101	Standard Epoxy Resin (EEW ~ 182)
Appearance		Clear, transparent	Yellow, transparent
Density@25°C	g/cm <sup>3</sup>	0.91	1.16
Viscosity@25°C	mPa*s	< 50	~ 13,000
Mixing ratio	(m/m)	26.1	100
Initial viscosity@30°C	mPa*s		~ 1000
Curing time@150°C	min		4 - 5

## HANDLING AND PROCESSING

- We recommend to preheat the resin to 30°C for better processing.  
All other ingredients can be applied at room temperature
- Optional: Mix the internal release agent and the resin
- Mix the hardener and the resin
- The mixture can be processed for at least 30 min
- Produced SMC sheets will solidify after ~6-8 h. They are still meltable at 60-80°C.
- The sheets have to mature for at least 3 days at 25°C. The maturation time can be reduced by increasing the maturation temperature. After maturation the SMC matrix will show a Tg of 45-55°C
- The sheets are storage stable for at least 8 weeks

Tab.2: Molding conditions for SMC sheets

	Unit	Value
Molding pressure	bar	100 - 200
Molding temperature	°C	150
Mold coverage	%	50 - 80
Curing time	min	3 - 4

Fig. 1: Shrinkage behavior of neat resin (method: volume dilatometry)





Fig. 2: Viscosity increase depending on temperature for matured SMC material



Tab. 3: Properties of cured neat resin system

	Unit	Value	Standard
Tensile modulus	MPa	2930	DIN EN ISO 527-2
Tensile stress at break	MPa	80	DIN EN ISO 527-2
Tensile strain at break	%	6	DIN EN ISO 527-2
Flexural modulus	MPa	2910	DIN EN ISO 178
Flexural strength	MPa	120	DIN EN ISO 178
Flexural strain at break	%	7	DIN EN ISO 178
Glass Transition temperature (Tg)	°C	120	DIN EN ISO 11357-2
Density	g/cm <sup>3</sup>	1.14	OECD 109

Tab. 4: Emission test of SMC panel

	Unit	Value	Standard
Volatile organic compounds	µg/g	9	PV 3341 / VDA 277

Marl, December 18, 2018; This data sheet replaces all former issues.

VESTALITE® is a registered trademark of Evonik Industrie AG or one of its subsidiaries.

**Disclaimer**

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

**EVONIK RESOURCE EFFICIENCY GMBH**  
 Business Line Crosslinkers  
 Paul-Baumann-Str. 1  
 45764 Marl  
 Germany

**EVONIK CORPORATION**  
 Business Line Crosslinkers  
 299 Jefferson Road,  
 Parsipanny, NJ 07054-0677  
 USA

**EVONIK SPECIALITY CHEMICALS  
 (SHANGHAI) CO., LTD.**  
 Business Line Crosslinkers  
 55, Chundong Road  
 Xinzhuang Industry Park  
 Shanghai, 201108  
 China

[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)  
 For contact in your country, please visit: [www.evonik.com/crosslinkers-contact](http://www.evonik.com/crosslinkers-contact)

