

BIS (PARA-AMINOCYCLOHEXYL) METHANE**GENERAL DESCRIPTION**

VESTAMIN PACM is a cycloaliphatic diamine which is manufactured by hydrogenation of methylene dianiline. It is a mixture of different isomers, and contains approximately 20 % of the trans, trans-PACM. It is a colorless low viscosity liquid with a faint amine odor.

SPECIFICATION

Property	Value	Unit	Test method*
Purity	≥ 99.0 (sum 2-ring amines)	% by wt.	gas chromatography
Trans-trans-4,4'-PACM	18 - 24	% by wt	gas chromatography
Appearance	clear liquid	-	visual
Color	max. 30 (APHA)	-	DIN EN ISO 6271
Water content	max. 0.1	% by wt	Karl-Fischer

PROPERTIES

VESTAMIN PACM can be used for all typical amine reactions, such as reaction with carboxylic acids, phosgene, aldehydes, ketones and epoxies.

VESTAMIN PACM combines the advantages of cycloaliphatic polyamines in epoxy systems: low mix viscosity, moderate reactivity and lower exothermic behaviour as well as the outstanding mechanical properties and excellent chemical resistance. In comparison to other amines, the sensitivity against carbamate formation is reduced, which is an advantage especially for epoxy hardeners.

APPLICATION

VESTAMIN PACM is used to produce hardeners for room temperature curing epoxies and as hardener in heat cured epoxies. Typical applications include epoxy curatives for composites and industrial floorings, and the production of specialty polyamides.

GENERAL CHEMICAL AND PHYSICAL COEFFICIENTS

Property	Value	Unit	Test method
Viscosity	29.6 (at 40°C) ²	mm ² /s	DIN 51 562, OECD 114
Molecular weight	201.3	g/mol	-
Amine value	535	mg KOH/g	DIN 16 945
H-active equivalent	52.6	g/val	
Solidification	(15) ³	°C	OECD 102
Boiling pt (1013 hPa)	320 ²	°C	OECD 103
Vapor pressure (20 °C)	≤ 0.01	hPa	OECD 104
Flash point	160	°C	DIN 51758
Relative density, d ²⁰	0.96	g/cm ³	OECD 109

TRANSPORT AND PACKAGING

VESTAMIN PACM is supplied in 180 kg non-returnable drums in Europe, Middle East and Africa as well as in Asia,
in 192 kg non-returnable drums in North-, Middle- and South America, and also in all regions in bulk.

*1 Mohr's balance

*2 Internal method

*3 The freezing point varies with isomer content, ranging from -17,7 to +65,4°C



STORAGE

VESTAMIN PACM is slightly hygroscopic and tends to form carbamates by reaction with atmospheric CO². It should be stored free from moisture and carbon dioxide in glass, stainless steel and carbon steel containers.

VESTAMIN PACM is stable for at least one year when stored in original containers at temperatures below 25°C.

VESTAMIN PACM crystallizes below 15°C. It is necessary to completely liquify the entire contents of the container by warming to a maximum of 60°C and mix thoroughly before use.

SAFETY AND HANDLING

Please refer to our Safety Data Sheet.

Marl, March 4, 2019; This data sheet replaces all former issues.

VESTAMIN® is a registered trademark of Evonik Industrie AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK RESOURCE EFFICIENCY GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

For contact in your country, please visit: www.evonik.com/crosslinkers-contact

EVONIK CORPORATION

Business Line Crosslinkers
299 Jefferson Road,
Parsipanny, NJ 07054-0677
USA

EVONIK SPECIALITY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

