

Product information

VESTANAT[®] EP* -M 222

(PRELIMINARY)

GENERAL DESCRIPTION

VESTANAT[®] EP-M 222 is a solvent based, polyfunctional methoxysilane which can be used as a co-crosslinker to increase the flexibility of stoving, highly scratch resistant enamels.

TYPICAL DATA

Property	Value	Unit	Test method
Viscosity at 23°C	3-5	Pas	DIN EN ISO 3219
Non-volatile constituent	85	% by wt.	calculated
NCO-content	≤ 0,1	% by wt	DIN EN ISO 11909, ASTM D 2572
Colour (Hazen)	≤ 50	mg Pt/l	DIN EN ISO 6271

PROPERTIES AND APPLICATIONS

VESTANAT[®] EP-M 222 is solved in butyl acetate and transparent. The co-crosslinker is used to increase the flexibility of VESTANAT[®] EP-M 95 based, scratch resistant stoving coatings for e.g. automotive (OEM, car refinish), plastic and maintenance applications.

* EP = Experimental Product

This is an experimental product at the development stage. No definitive statements can therefore be made as to type conformity, processability, long-term performance characteristics or other production or application parameters. Therefore, the purchaser/user uses the product entirely at its own risk without having been given any warranty or guarantee and agrees that the supplier shall not be liable for any damage, of whatever nature, arising out of such use. The figures given should be regarded as non-binding approximate data only, and not as guide values or binding minimum values. Commercialization and continued supply of this product are not assured. Its supply may be discontinued at any time.

STORAGE AND PACKAGING

VESTANAT® EP-M 222 is an experimental and therefore final information on storage stability isn't yet available. Due to the fact that the product is sensitive to moisture we advise to store VESTANAT® EP-M 222 in a tightly sealed container to avoid an increased entry of water for re-use. Due to the fact that the product is sensitive to elevated temperatures we advise to store VESTANAT® EP-M 222 at room temperature to avoid an increased yellowing.

SAFETY AND HANDLING

The formation of methanol during curing must be taken into consideration. Provisions to protect workers have to be installed.

For further information on the safe handling of VESTANAT® EP-M 222 please refer to our safety data sheet.

Marl, June 10, 2018; This data sheet replaces all former issues.

VESTANAT® is a registered trademark of Evonik Industrie AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK RESOURCE EFFICIENCY GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

For contact in your country, please visit: www.evonik.com/crosslinkers-contact

EVONIK CORPORATION

Business Line Crosslinkers
299 Jefferson Road,
Parsippany, NJ 07054-0677
USA

EVONIK SPECIALITY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

