

VESTANAT[®] EP*-U 523**GENERAL DESCRIPTION**

VESTANAT[®] EP-U 523 is an aliphatic PUR-prepolymer dissolved in 1-methoxy-2-propyl acetate. It is used to formulate lightfast and weathering resistant coatings.

SPECIFICATION (PRELIMINARY)

Property	Value	Unit	Test method*
Solid content	80 ± 1	% by wt.	DIN EN ISO 3251 (1,2-1,5 g, 1 h 150°C)
Viscosity at 23°C	~ 7000	mPas	DIN EN ISO 3219
NCO content	2.9 ± 0.2	% by wt.	DIN EN ISO 11909

TYPICAL DATA

Property	Value	Unit	Test method
Monomer Content (IPDI)	≤ 0.8	% by wt.	DIN EN ISO 10283
Colour number (Hazen)	≤ 100	-	DIN EN ISO 6271
Density (20°C)	1.049	g/cm ³	DIN 51757
Flash point	44	°C	DIN EN ISO 13736

* EP = Experimental Product

This is an experimental product at the development stage. No definitive statements can therefore be made as to type conformity, processability, long-term performance characteristics or other production or application parameters. Therefore, the purchaser/user uses the product entirely at its own risk without having been given any warranty or guarantee and agrees that the supplier shall not be liable for any damage, of whatever nature, arising out of such use. The figures given should be regarded as non-binding approximate data only, and not as guide values or binding minimum values. Commercialization and continued supply of this product are not assured. Its supply may be discontinued at any time.

PROPERTIES AND APPLICATIONS

Due to its aliphatic PUR-character, VESTANAT® EP-U 523 is used as a binder for moisture curing, light- and weather resistant polyurethane/polyurea coatings, in combination with VESTANAT® T 1890 M.

STORAGE

VESTANAT® EP-U 523 is supplied in non-returnable 200 kg net drums. VESTANAT® EP-U 523 can be stored in unopened containers for at least 6 months without loss of quality in accordance with the above specification.

SAFETY AND HANDLING

Please refer to our Material Safety Data Sheet.

Marl, February 12, 2019; This data sheet replaces all former issues.

VESTANAT® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK RESOURCE EFFICIENCY GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

For contact in your country, please visit: www.evonik.com/crosslinkers-contact

EVONIK CORPORATION

Business Line Crosslinkers
299 Jefferson Road,
Parsipanny, NJ 07054-0677
USA

EVONIK SPECIALITY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

