

VESTANAT[®] T 1890 X

GENERAL DESCRIPTION

VESTANAT[®] T 1890 X is a polyisocyanate based on isophorone diisocyanate solubilized in Benzene, 1-chlorobenzene-4 (Trifluormethyl)/Oxsol** 100 to a solids Level of 55 % by weight.

SPECIFICATION

Property	Value	Unit	Test method*
Solids content	55 ± 1	% by wt.	DIN EN ISO 3251 (1 h, 150°C)
Non volatile matter	9.5 ± 0.3	% by wt.	DIN 53 185 / ASTM D 2572 / DIN ISO 11909
Viscosity at 23 °C	550 ± 150	mPas	DIN 53 019 / DIN EN ISO 3219

TYPICAL PROPERTIES

Property	Value	Unit	Test method
Density at 15 °C	1.23	g/cm ³	DIN 51 757 / ASTM D 2111
Colour (APHA)	< 250	-	DIN ISO 6271
Flash point (closed Cup)	43	°C	DIN EN ISO 1523
VESTANAT [®] IPDI	0.2	% by wt.	DIN 55 956 / DIN ISO 10 283

* DIN, ISO or ASTM methods describe our analytical procedures in general. The actual methods used internally are more precise and can be obtained upon

**Oxol is a trade Name of Oxychem Corporation.

PROPERTIES AND APPLICATIONS

VESTANAT[®] T 1890 X meets all important prerequisites for the production of weatherable two component polyurethane coatings. With suitable coreactants it gives Polyurethane coatings with high resistance to yellowing from sunlight and excellent environmental etch resistance, as well as the good mechanical properties typical of polyurethane coatings.

APPLICATION

VESTANAT® T 1890 X is used as the isocyanate component for the production of hardeners for two component polyurethane coatings. These coatings are used in automotive repair clearcoats and other applications requiring excellent surface quality, high gloss, environmental etch resistance and weatherability.

SAFETY AND HANDLING

For Information on safety and handling, consult the Material Safety Data Sheet for this product.

STORAGE AND PACKAGING

If moisture is excluded, this product can be stored for at least one year without loss of Quality. VESTANAT® T 1890 X is supplied in non-returnable drums and in bulk.

Marl, June 10, 2018; This data sheet replaces all former issues.

VESTANAT® is a registered trademark of Evonik Industrie AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK RESOURCE EFFICIENCY GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

For contact in your country, please visit: www.evonik.com/crosslinkers-contact

EVONIK CORPORATION

Business Line Crosslinkers
299 Jefferson Road,
Parsippany, NJ 07054-0677
USA

EVONIK SPECIALITY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

